

ROAD COMMISSION FOR OAKLAND COUNTY

SPECIAL PROVISION  
FOR  
**CALCIUM CHLORIDE**

RCOC/DESIGN:AP/JO

PAGE 1 OF 1

RCOC20SP850C  
ORG:04-05-21

**a. Description**

This work consists of furnishing and placing calcium chloride according to the plans and section 305 of the *Michigan Department of Transportation 2020 Standard Specifications for Construction* except as herein provided.

**b. Materials**

26%-40% calcium chloride well brine.

**c. Construction**

Upon completion of pulverizing/crushing HMA pavement, evenly apply two coats of well brine calcium chloride at a rate of 0.25 gallons/syd. Rough grade the crushed material and obtain plan cross section. Apply third coat of calcium chloride at a rate of 0.25 gallons/syd. Final grade required cross section and compact to crushed material.

**d. Measurement and Payment**

The completed work, as described, will be measured and paid for at the contract unit price using the following pay item:

<b>Pay Item</b>	<b>Pay Unit</b>
Calcium Chloride.....	Gallon

**Calcium Chloride** includes equipment, labor and materials to place material, as described, and will be paid by plan quantity.